

Original Research Article

## The Effects of Artificial saliva and fluoride varnish on Microhardness of Bleached Enamel with 40% Hydrogen Peroxide-An Invitro Study

**\*Somayeh Hosseini Tabatabaei<sup>1</sup>, Sadegh Nakhzari<sup>2</sup>, Mohammad Naebi<sup>3</sup>**<sup>\*1</sup>Assistant professor of operative dentistry, oral and dental disease research center, Zahedan university of medical science, Zahedan, Iran<sup>2</sup>School of Dentistry, Zahedan University of Medical Science, Zahedan, Iran<sup>3</sup>School of Dentistry, Tabriz University of Medical Science, Tabriz, Iran**\*Corresponding author**

Mohammad Naebi

Email: [mohammadnaeyebi2000@gmail.com](mailto:mohammadnaeyebi2000@gmail.com)

**Abstract:** Teeth whitening have been accepted as one of the most conservative treatment methods of discolored teeth, however, these materials have also some complications for teeth. The aim of this study was to investigate the effect of artificial saliva and fluoride varnish on microhardness of bleached enamel with 40% hydrogen peroxide. Twenty intact extracted human anterior teeth were selected. Once the initial preparation of the teeth, they were divided into two groups randomly. Primary microhardness of enamel was measured by Vickers test. Then both groups separately were bleached with 40% hydrogen peroxide, and microhardness was measured again. In the next step, first group was stored in artificial saliva (AS) and fluoride varnish was used in second group. The microhardness was measured again. Data were analyzed with Paired T- test at a significant level of  $P < 0.05$ . In both groups, enamel microhardness was decreased after bleaching, this reduction was not significant in the first (AS) group, while it was significant in the second (fluoride) group ( $P = 0.3$  in AS group,  $P = 0.03$  in fluoride group). Moreover, the artificial saliva ( $P = 0.05$ ) and fluoride ( $P = 0.004$ ), increased the enamel microhardness after bleaching. Based on this study, artificial saliva and fluoride can increase the enamel microhardness.

**Keywords:** Hydrogen peroxide-Microhardness- Fluoride.**INTRODUCTION**

The smile is one of the most important factors in social relationships [1]. White teeth increase self-confidence and improve their social eminence [2]. Hence, now a days, patients' demand have increased for esthetic dentistry treatments [1]. There are different ways to achieve this goal, such as composite restorations, ceramic crowns or laminates. But, these treatments can cause loss of tooth structure and change the normal contour of the tooth. In modifying of dental discolorations, tooth bleaching treatments are easier, more acceptable, economical and conservative [4 & 3].

There are three basic methods for whitening vital teeth: In office, At home and bleaching with Over the counter products (OTC). Bleaching can be done with different materials such as hydrogen peroxide, carbamide peroxide, sodium perborate which can be used with different concentrations [5]. These materials

diffuse through the organic matrix of tooth structure due to low molecular weight [1, 6]. The attack of hydrogen peroxide in organic matrix leads to destruction of the long organic chains into colorless short chains during the oxidation process [1].

Some studies reported the complications of bleaching agents include: Changes in the chemical composition of teeth, changes in the mineral content of dental structures such as calcium and phosphate, changes in enamel fluoride content, topographic changes, increase in enamel porosity, opening enamel prisms, effects similar to etched enamel [3, 7, 8], reducing the enamel microhardness [6, 9, 10], opening the dentinal tubules and increasing dentin sensitivity [6], as well as, in some studies, changes in the morphology and composition of the enamel were observed, which were also not limited to the surface and can be seen in the subsurface layers of enamel [8].

Based on the hydrodynamic theory, the movement of fluid within the dentinal tubules stimulates receptors and creates pain. If bleaching agents are along with desensitising materials such as potassium nitrate and fluoride, this problem is reduced [6].

The fact that topical application of fluoride is effective in progressing and retrieving of the minerals and preventing the reduction of them [11,12]. Fluoride compounds may support the recovering microstructure defects resulted from bleaching of the teeth with absorption and deposition of salivary compounds such as calcium and phosphate [13]. In a study, hardness of enamel was reduced in all groups through applying carbamide peroxide and but use of fluoride, and calcium increased the microhardness [14].

In a study in 2012, the effects of brushing with toothpaste, on microhardness of bleached enamel with 15% carbamide peroxide were evaluated. The results showed that brushing immediately and 1-2 hours after bleaching have no effect on the enamel microhardness [7]. Also, in one study, The enamel specimens treated with CCP-ACP topical paste showed smoother surfaces than those used fluoride dentifrice [15]. Some studies have been performed on the adverse effects of different bleaching materials on the dental tissues as well as on the effects of mineralized agents on the enamel microhardness, however existing studies have shown different results [2,6,7,10,13-17]. Due to the daily increase of the use of bleaching materials and some of their effects on dental tissues, we decided to assess the effects of these materials on the enamel. Hence, the aim of this study is to investigate the effects of artificial saliva and fluoride on the microhardness of bleached enamel with 40% hydrogen peroxide.

## MATERIALS AND METHODS

Twenty intact extracted human anterior teeth were selected based on inclusion and exclusion criteria. They were extracted due to the orthodontics, periodontal diseases or missing reasons, so that they were without any cracks, caries, filling and buccal, lingual, incisal wears, without discolorations with internal or external origins of congenital imperfections

such as fluorosis in visual examination. The teeth were washed thoroughly after being extracted and were kept in distilled water at room temperature until the tests. The specimens were cleaned by scaling instrument and rubber cap and fluoride-free pumice powder. Teeth were mounted in the self-curing acrylic resin (Acropars, Iran), so that the lingual side of the teeth was into the acrylic and the labial side was out of it. The crowns of teeth were polished with diamond polishing disks (Brazil-FGM). Each disk was used for five cases.

Specimens were divided into two groups randomly. The microhardness of baselines was measured by Vickers Hardness Testing Machine, in such that, the area of load entering was the central part of the buccal surface of the tooth. The load was 100 gram per 10 seconds. Three Indents of microhardness were measured in each specimen and the average indent was recorded. Both groups were treated with 40% hydrogen peroxide (Opalescence Boost / Ultradent / USA) separately according to the manufacturer's instructions. The buccal surface of each tooth, was covered with 2 mm thickness of this material for 15 minutes separately and then was cleaned with cotton and it was repeated twice, each for 15 minutes to 45 minutes. The gel was removed from the teeth by cotton and washed with distilled water. At this stage, enamel microhardness was measured again, in the same conditions were performed.

In the next phase, first group was stored in artificial saliva for 4 hours, and 5% sodium fluoride varnish (Flor Opal Varnish / Ultradent / USA) was used for the second group, according to the manufacturer's instructions. Then the microhardness of both groups were measured again. SPSS 20 software was used for data analyzing and Paired-T test was used to compare the mean microhardness of enamel in the first (AS) and second (fluoride) groups, before and after bleaching and after exposed to fluoride and artificial saliva.

## RESULTS

This study aimed to evaluate the effect of artificial saliva and fluoride on microhardness of bleached enamel with 40% hydrogen peroxide.

**Table 1: Comparison of enamel microhardness in both groups, before and after bleaching**

Micro Hardness group	before bleaching	After bleaching	P- value
	Mean±SD	Mean±SD	
Artificial saliva	400.1±47.3	366.5 ± 65	0.3
Fluoride varnish	226.5±32.46	189.52 ± 32.46	0.03

According to the results presented in Table 1, the average primary microhardness of enamel (before bleaching) in the first (AS) group was  $400.1 \pm 47.3$  and the enamel microhardness after bleaching was  $366.5 \pm 65$ , comparing the microhardness of two stages was not significant ( $P = 0.3$ ). As well as, the average primary microhardness of enamel in the second (fluoride)

group was  $226.5 \pm 3.4$  and the enamel microhardness after bleaching was  $189.52 \pm 32.46$ , while comparing of microhardness of two stages of these groups was significant ( $P = 0.03$ ). Then, the average microhardness after bleaching and after exposure in remineralized agents were compared on the basis of  $P \leq 0.05$  (Table 2).

**Table 2: Comparison of enamel microhardness in group, after bleaching and expose to remineralizing material**

Micro Hardness Group	After bleaching	Remineralised Material	P- value
	Mean±SD	Mean±SD	
Artificial saliva	366.5±65	398±53	0.3
Fluoride varnish	189.52± 32.46	249.91±39.08	0.03

Based on the results presented in Table 2, the average microhardness of enamel after bleaching in the first (AS) group was  $366.5 \pm 65$  and it was  $398 \pm 53$  after immersion in AS. The average microhardness of enamel after bleaching in the second (fluoride) group was  $189.52 \pm 32.46$  and it was  $249.91 \pm 39.08$  after exposed to fluoride, which the differences of microhardness were significant in two stages of the two groups ( $P = 0.05$ ).

## DISCUSSION

In the present study, the mean microhardness of enamel in the AS group was  $400.1 \pm 47.3$  and in the fluoride group was  $226.5 \pm 3.4$ . Difference in the initial microhardness is resulted from different degrees of enamel mineralization with local variations of enamel tissue and enhance in the porosity near DEJ area. In addition, the microhardness is reduced from the outer surface to the DEJ [18]. As well as, the enamel microhardness is different in other studies, so that consistency in measuring techniques can be referred in addition to pre-mentioned factors. The use of Vickers hardness test or Knoop hardness, the amount and duration of load in enamel microhardness measurement, microhardness measurement of surface or subsurface enamel, using of human or bovine teeth specimens, anterior or posterior teeth, can cause discrepancies in these studies [4]. In this study, microhardness of human teeth was measured by Vickers test, under the force of 100 g per 10 seconds. As well as the factors such as environmental factors, the fluoridation of drinking water, dental age and different habits in some countries

could also affect the primary microhardness of enamel [19]. The first part of results showed that applying 40% hydrogen peroxide bleaching material in the offices could reduce the enamel microhardness, so that the reduction was not significant in the AS group while it was significant in the fluoride group. (AS group  $P = 0.3$  and fluoride group  $P = 0.03$ ).

The results of the first group (AS) of this study were consistent with the study of Shannon *et al.*; (10% CP Carbamide peroxide) [20], Seghi *et al.*; (10% CP) [21], Cadenaro *et al.*; (38% HP) [22], Suleiman *et al.*; (35% HP) [23], Smidt *et al.*; (15- 16% CP) [24] and study of Davari *et al.*; (10CP and 22%) [2], and they were inconsistent with the results of the second group (fluoride). On the other hand, the results of the first group were inconsistent with results of Feagin *et al.*; [25] Soldani *et al.*; [26], Rodrigues *et al.*; [27], Basting *et al.*; [28], Efeoglu *et al.*; [29], McGuckin *et al.*; [30], Efeoglu *et al.*; [31], Tezel *et al.*; [32] and a part of Borges *et al.*; studies [9], while they were consistent with the results of the second group (fluoride).

It should be noted that in our study also the reduction of enamel microhardness has occurred in both groups, in other words, the mineral content of enamel has been partly reduced because hydrogen peroxide had oxidation effect on the enamel organic matrix [5,18]. So that Potocnik *et al.*; demonstrated that the application of 10% carbamide peroxide causes micro structural

changes but does not cause changes in enamel hardness [19], this may have also occurred in this work in the first group. However, due to the presence of 1.1 % fluoride and 3% potassium nitrate (desensitising agents) in combination with this bleaching material and PH of 7, the effects of bleach on the reduction of enamel microhardness have been modified. Since Attin *et al.*; [13] showed that the addition of fluoride to the bleaching agents leads to re-hardening of the bleached enamel.

The reasons for conflicting with other studies include the following: different bleaching materials, differences in PH level [24], the frequency and duration use of bleaching material, oxidative effects of bleaching agents, the amount of bleaching thickeners for stability of the material [33], the presence of fluoride and desensitising agents [34], the variation in the morphology of the enamel [22], differing experimental tests and dental specimens (human / bovine) [4] and the less number specimens [2]. The results showed that the use of fluoride at the second group and use of artificial saliva in the first group after bleaching of teeth, lead to an increase in microhardness, which is significant (AS group  $P= 0.05$  and the fluoride group  $P= 0.004$ ).

These results were aligned with the results of Bizhang *et al.*; [4], Burlamaqui Pinheiro *et al.*; [6], Borges *et al.*; [9], Borges *et al.*; [10], Attin *et al.*; [13], Chen *et al.*; [16]. The presence of fluoride ions around teeth leads to deposit the fluoro-apatite from calcium and phosphate ions in saliva, and fluoride increases the resistance of tooth tissue against demineralization. As well as fluoride was replaced by dissolved ions containing magnesium and carbonate which were lost during the demineralization, and this displacement process causes more resistant of the enamel. The presence of high concentrations of fluoride level may act as a reservoir for fluoride that promotes remineralization [35]. However, the results of this work was inconsistent with the study of Davari *et al.*; [2]. So that in the study of Davari the use of fluoride toothpaste at a concentration of 1450ppm did not increase the microhardness after bleaching with 10 % carbamide peroxide. While in the same work, using the same toothpaste increased the enamel microhardness after bleaching with 22% carbamide peroxide [2]. In this regard, according to Ulukapi *et al.*; [36] and Davari *et al.*; [2] it can be noted that higher concentrations of carbamide peroxide due to more solubility properties of minerals in the enamel, increase the potential of fluoride absorption.

In addition, our survey also was in conflict with another part of the Davari *et al.* study. So that in the study of Davari the application of Tooth Mousse paste containing PPM 900 fluoride decreased the enamel microhardness after bleaching with 22% carbamide peroxide and it was ineffective in the use of 10% carbamide peroxide, that's probably due to the presence of 0.2- 0.3 % phosphoric acid in Tooth Mousse paste. The storage of the specimens in the artificial saliva led to enhance microhardness. Formulation of artificial saliva used in this study was according to the study of Amaechi *et al.*; [37] with PH of 7. This study was consistent with Amaechi *et al.*; [36], and Gelhard *et al.*; [38], Lussi *et al.*; [39] studies. Artificial saliva contains chemical compounds such as potassium chloride, magnesium chloride, calcium chloride, di potassium hydrogen phosphate, potassium dihydrogen phosphate, which may improve the enamel remineralization [18]. While it was inconsistent with some other studies, including Borges *et al.*; [10] (in their studies the artificial saliva had no effects on enamel hardness), which the conflict was associated with the difference in artificial saliva formula, immersion time, the type of teeth and different study designs. It should be noted that with  $P = 0.05$  in this study, if more specimens were tested, the results would be also altered.

## CONCLUSIONS

Although the present study couldn't completely mimic oral environment, the results showed that bleaching agents used in this research can reduce the microhardness of enamel. Also, the Fluoride and artificial saliva had remineralization effects on the bleached enamel. However, further studies using demineralized agents, associated with the effect of oral environment are required.

## REFERENCES

1. Abouassi T, Wolkewitz M, Hahn P. Effect of carbamide peroxide and hydrogen peroxide on enamel surface: an in vitro study. *Clinical Oral Investigations*. 2011 Oct 1; 15(5):673-80.
2. Davari AR, Kazemi AD, Ataei E, Vatanpour M, Abdollahi H. Effects of Bleaching and Remineralising Agents on the Surface Hardness of Enamel. *Journal of Dentistry, Shiraz University of Medical Sciences*. 2012 Jul 1; 13(4):156-63.
3. Worschech CC, Rodrigues JA, Martins LR, Ambrosano GM. In vitro evaluation of human dental enamel surface roughness bleached with 35% carbamide peroxide and submitted to abrasive dentifrice brushing. *Pesquisa Odontológica Brasileira*. 2003 Dec; 17(4):342-8.

4. Bizhang M, Seemann R, Duve G, Römhild G, Altenburger MJ, Jahn KR, Zimmer S. Demineralization effects of 2 bleaching procedures on enamel surfaces with and without post-treatment fluoride application. *Operative Dentistry*. 2006 Nov; 31(6):705-9.
5. Tabatabaei SH, Tabatabaei MR, Naebi M. Research Article the Effect of Bleaching Agents on Micro Chemical Structure of Human Enamel by FTIR Spectroscopy Method (An in-vitro study).
6. Pinheiro HB, Lopes B, Klautau EB, Cardoso J, Silva BR, Cardoso PE. Influence of bioactive materials used on the dentin surface whitened with carbamide peroxide 16%. *Materials Research*. 2010 Jun; 13(2):273-8.
7. Navimipour EJ, Kimyai S, Nikazar S, Ghojzadeh M. In vitro evaluation of the effect of delaying toothbrushing with toothpaste on enamel microhardness subsequent to bleaching the teeth with 15% carbamide peroxide. *Operative dentistry*. 2012 Jan; 37(1):87-92.
8. Pinto CF, Leme AF, Cavalli V, Giannini M. Effect of 10% carbamide peroxide bleaching on sound and artificial enamel carious lesions. *Brazilian dental journal*. 2009; 20(1):48-53.
9. Borges BC, Borges JS, De Melo CD, Pinheiro IV, Santos AD, Braz R, Montes MA. Efficacy of a novel at-home bleaching technique with carbamide peroxides modified by CPP-ACP and its effect on the microhardness of bleached enamel. *Operative dentistry*. 2011 Oct; 36(5):521-8.
10. Borges AB, Yui KC, D'Avila TC, Takahashi CL, Torres CR, Borges AL. Influence of remineralizing gels on bleached enamel microhardness in different time intervals. *Operative Dentistry*. 2010 Mar; 35(2):180-6.
11. Cate JT. In vitro studies on the effects of fluoride on de-and remineralization. *Journal of Dental Research*. 1990 Feb; 69(2\_suppl):614-9.
12. Murchison DF, Charlton DG, Moor BK. Carbamide peroxide bleaching effects on enamel surface hardness and bonding. *Oper Dent J*. 1992 Sep-Oct; 17(5):181-185.
13. Attin T, Betke H, Schippan F, Wiegand A. Potential of fluoridated carbamide gels to support post-bleaching enamel re-hardening. *J Dent*. 2007 Sep; 35(9):755-759
14. Cavalli V, Rodrigues LK, Paes-Leme AF, Brancalion ML, Arruda MA, Berger SB, Giannini M. Effects of bleaching agents containing fluoride and calcium on human enamel. *Quintessence International*. 2010 Sep 1; 41(8).
15. De Souza CC, Cury JL, Coutinho TC, Da Silva EM, Tostes MA. Effect of different application frequencies of CPP-ACP and fluoride dentifrice on demineralized enamel: a laboratory study. *Am J Dent*. 2014 Aug; 27(4):215-9
16. Chen Hp, Chang CH, Liu Jk, Chuang SF, Yarnng Jy. Effect of fluoride containing bleaching agents on enamel surface properties. *Dent J*. 2008 Sep; 36(9):718-25.
17. Borges AB, Samezima LY, Fonseca LP, Yui KC, Borges AL, Torres CR. Influence of potentially remineralizing agents on bleached enamel microhardness. *Operative Dentistry*. 2009 Sep; 34(5):593-7.
18. Panich M, Poolthong S. The effect of casein phosphopeptide-amorphous calcium phosphate and a cola soft drink on in vitro enamel hardness. *The Journal of the American Dental Association*. 2009 Apr 30; 140(4):455-60.
19. Potočnik I, Kosec L, Gašperšič D. Effect of 10% carbamide peroxide bleaching gel on enamel microhardness, microstructure, and mineral content. *Journal of endodontics*. 2000 Apr 30; 26(4):203-6.
20. Shannon H, Spencer P, Gross K, Tira D. Characterization of enamel exposed to 10% carbamide peroxide bleaching agents. *Quintessence international*. 1993 Jan 1; 24(1).
21. Seghi RR, Denry I. Effects of external bleaching on indentation and abrasion characteristics of human enamel in vitro. *Journal of Dental Research*. 1992 Jun; 71(6):1340-4.
22. Cadenaro M, Navarra CO, Mazzoni A, Nucci C, Matis BA, Di Lenarda R, Breschi L. An in vivo study of the effect of a 38 percent hydrogen peroxide in-office whitening agent on enamel. *The Journal of the American Dental Association*. 2010 Apr 30; 141(4):449-54.
23. Sulieman M, Addy M, Macdonald E, Rees JS. A safety study in vitro for the effects of an in-office bleaching system on the integrity of enamel and dentine. *Journal of Dentistry*. 2004 Sep 30; 32(7):581-90.
24. Smidt A, Feuerstein O, Topel M. Mechanical, morphologic, and chemical effects of carbamide peroxide bleaching agents on human enamel in situ. *Quintessence International*. 2011 May 1; 42(5).
25. Feagin F, Koulourides T, Pigman W. The characterization of enamel surface demineralization, remineralization, and associated hardness changes in human and bovine material. *Archives of oral biology*. 1969 Dec 1; 14(12):1407-17.
26. Soldani P, Amaral CM, Rodrigues JA. Microhardness evaluation of in situ vital bleaching and thickening agents on human dental enamel.

- International Journal of Periodontics & Restorative Dentistry. 2010 Mar 1; 30(2).
27. Rodrigues JA, Marchi GM, Ambrosano GM, Heymann HO, Pimenta LA. Microhardness evaluation of in situ vital bleaching on human dental enamel using a novel study design. *Dental Materials*. 2005 Nov 30; 21(11):1059-67.
28. Basting RT, Rodrigues AL, Serra MC. The effect of 10% carbamide peroxide, carbopol and/or glycerin on enamel and dentin microhardness. *Operative Dentistry-University Of Washington*. 2005 Sep 1; 30(5):608.
29. Efeoglu N, Wood D, Efeoglu C. Microcomputerised tomography evaluation of 10% carbamide peroxide applied to enamel. *Journal of dentistry*. 2005 Aug 31; 33(7):561-7.
30. McGuckin RS, Babin JF, Meyer BJ. Alterations in human enamel surface morphology following vital bleaching. *The Journal of prosthetic dentistry*. 1992 Nov 1; 68(5):754-60.
31. Efeoglu N, Wood DJ, Efeoglu C. Thirty-five percent carbamide peroxide application causes in vitro demineralization of enamel. *Dental Materials*. 2007 Jul 31; 23(7):900-4.
32. Tezel H, Ertas OS, Ozata F, Dalgat H, Korkut ZO. Effect of bleaching agents on calcium loss from the enamel surface. *Quintessence international*. 2007 Apr 1; 38(4).
33. Sun L, Liang S, Sa Y, Wang Z, Ma X, Jiang T, Wang Y. Surface alteration of human tooth enamel subjected to acidic and neutral 30% hydrogen peroxide. *Journal of dentistry*. 2011 Oct 31; 39(10):686-92.
34. Bistey T, Nagy IP, Simó A, Hegedűs C. In vitro FT-IR study of the effects of hydrogen peroxide on superficial tooth enamel. *Journal of dentistry*. 2007 Apr 30; 35(4):325-30.
35. Roberson T, Heymann HO, Swift Jr EJ. *ARABIC-Sturdevant's Art and Science of Operative Dentistry: Arabic Bilingual Edition*. Elsevier Health Sciences; 2013 Dec 2.
36. Ulukapi H. Effect of different bleaching techniques on enamel surface microhardness. *Quintessence International*. 2007 Apr 1; 38(4).
37. Amaechi BT, Higham SM, Edgar WM. Factors influencing the development of dental erosion in vitro: enamel type, temperature and exposure time. *Journal of oral rehabilitation*. 1999 Aug 1; 26(8):624-30.
38. Gelhard TB, Fidler V, Vissink A. Remineralization of softened human enamel in mucin-or CMC-containing artificial salivas. *Journal of Oral Pathology & Medicine*. 1983 Sep 1; 12(5):336-41.
39. Lussi A, Megert B, Eggenberger D, Jäggi T. Impact of different toothpastes on the prevention of erosion. *Caries Research*. 2008; 42(1):62-7.